



**Clevedale  
Bawtry Road  
Austerfield  
Doncaster  
DN10 6QW**

**Phone: 01302 714517**

**Email: Sales@keyabrasives.co.uk**

**Website: www.keyabrasives.co.uk**

10/02/2022

## Technical Data

### Steel Shot

They clean by hammering action. The profile they produce is much rounder than that achieved by similar shot of iron abrasives. Providing a muted finish to metal.

The important point to remember is to choose an abrasive of the lowest hardness needed to achieve the profile and speed of cleaning required.

The harder the abrasive, the shorter life because of its tendency to fracture more quickly. It means higher abrasive costs and increase wear on machine parts.

Grade	Particle size (mm)
S70	0.18 – 0.35
S110	0.3 - 0.5
S170	0.42 – 0.71
S230	0.6 - 0.85
S330	0.85 -1.2
S390	1.0 – 1.4
S460	1.2 – 1.7
S550	1.4 – 2.0
S660	1.7 – 2.4
S780	2.0 – 2.8

Packed in 25 kilo plastic bags shrink wrapped on pallets.

Hardness ; 390 - 530 HV

Produced to ISO Standard 11124 part 3

Tariff Code; 7205100000